

Model: AG1000Application:

AG1000 activated carbon is a virgin activated carbon. It is granular in form. Its ideal is for many liquid phase applications including the removal of taste and odor compounds and dissolving organics from water stream.

Specification:

		ASTM TEST METHODS
Mesh Size:	6x16, 12x40, 8x30, 20x50 Oversize: 5% max. Undersize: 5% max.	
Ash(WT%):	18 % typical.	D2866-94
Moisture:	5% max.	D2867-91
Hardness No.	90 min.	D3802-79
Iodine No.	1000 mg/g min.	D4607-94
Apparent Density:	0.44 - 0.55g/ml	D2854-94
Abrasion:	80min.	B604
Water Soluble Ash:	0.3 max.	

Packaging:

Material to be packed in black super sacks with 500kg or 1100lb net each, 2 sacks per pallet. 20-25kg small bags are available.

Remarks:

The above specification can be adjusted in accordance with the customer's requirement.